

High Pressures, Low Temperatures, and Magnetic Field Effects on AgFeAsSe_3 and AgFeSbSe_3 Properties

O. L. Kheifets, L. L. Nugaeva, A. V. Tebenkov, A. S. Volegov, E. F. Shakirov, N. V. Melnikova, and A. N. Babushkin

Ural Federal University, Yekaterinburg, 620000 Russia

e-mail: olga.kobeleva@usu.ru

Abstract—A procedure for synthesizing AgFeAsSe_3 and AgFeSbSe_3 is presented, and their electric and magnetic properties are investigated over a wide range of temperatures, pressures, and magnetic field variation. At 100–400K, the samples are characterized by semiconductor properties. Under pressures of ~25 and ~24 GPa, the electric properties of AgFeAsSe_3 and AgFeSbSe_3 change greatly.

DOI: 10.3103/S1062873813030179

INTRODUCTION

It is of interest to synthesize multicomponent semiconductors based on silver and copper chalcogenides, and to investigate their electrical, magnetic and mechanical properties under extreme conditions (low temperatures, high pressures and magnetic fields presence) [1–5]. The synthesis and electric and magnetic properties of AgFeAsSe_3 and AgFeSbSe_3 over a wide range of temperatures, pressures, and magnetic field variation are examined in this work.

EXPERIMENTAL

Our samples were synthesized using the ampoule technique. According to X-ray structural analysis, the synthesized materials were a mixture of two phases: FeSe and AgBSe_2 ($B = \text{As, Sb}$). The relationship between impedance and temperature was investigated by impedance spectroscopy using an RCL-2010 impedance analyzer for frequencies ranging from 1 kHz to 1 MHz and temperatures from 78 K to 400 K. A high-pressure chamber with an polycrystalline diamond (carbonado) anvil of the rounded cone–plane type was used to generate high pressures [6]. AgFeAsSe_3 magnetization was measured on a MPMS XL7 SQUID magnetometer at temperatures ranging from 100 to 400K and under magnetic fields of up to 7 T.

Figure 1 shows the impedance hodographs for the investigated compounds at a temperature of 300K. In the high-frequency part, the hodographs can be approximated by a circular arc. To investigate the compounds' electric conductivity and dielectric permeability, we selected frequencies of 93 kHz and 200 kHz, which are higher than the boundary fre-

quency that separates the area of electrode processes and the area where we can ignore boundary effects.

Figure 1b shows the temperature dependences for electric conductivity and dielectric permeability measured at 200 Hz. The temperature dependence of AgFeAsSe_3 is of the activation type and the energy of activation changes between 240–280K. In the temperature range of 220–250K, we can see an anomaly in the relationship between temperature and resistance. The same anomaly is observed for direct current at temperatures of 260–270 K [7]; i.e., if the frequency is raised, the anomaly drifts toward lower temperatures. The dielectric permeability rises if the temperature is raised, and upon heating at a frequency of 200 Hz we observe a small maximum at a temperature of ~240 K. When measuring at a frequency of 93 Hz, however, this maximum is virtually stable. The relationship between electric conductivity and temperature for AgFeSbSe_3 is of the activation type and the energy of activation changes at 220K.

Figure 2a shows the relationships between magnetization and temperature for AgFeAsSe_3 in fields of 4 T and 7 T. It can be seen that magnetization diminishes at temperatures of up to ~310K, and if the temperature is lowered more, it is virtually stable. This could be because the sample transitions from the paramagnetic state to a state with magnetic ordering at temperatures lower than 310 K. These results agree with the results obtained for lower fields and temperatures. We investigated how magnetization depends on the magnetic field and we found that if the field grows, magnetization also rises but saturation is not achieved in fields lower than 7 T. The curves corresponding to the field diminishing and field growing coincide at fields higher than 0.5 T (Fig. 2b).




Fig. 1. (a) Hodograph for impedance and temperature curves for (b) electric conductivity and (c) dielectric permeability for AgFeAsSe₃ and AgFeSbSe₃.




Fig. 2. Relationship (a) between temperature and magnetization and (b) between magnetization and field for AgFeAsSe₃.

Figure 3a shows the relationship between pressure and the resistance of AgFeAsSe₃ and AgFeSbSe₃ at 300 K. If the pressure increase, AgFeAsSe₃ resistance falls to 25 GPa and is virtually constant after that. Perhaps a phase transition takes place in this pressure region. For AgFeSbSe₃, resistance drops sharply in the area of 24 GPa. To determine its regions of existence we investigated the relationship between pressure and resistance for magnetic fields lower than 1 T. It was found that the magnetic field influences sample resistance in the area of the assumed phase transition and not beyond it (Fig. 3b).

CONCLUSIONS

Our AgFeAsSe₃ and AgFeSbSe₃ samples were characterized by semiconductor properties at temperatures of 100–400 K, and there was an anomaly on the $R(T)$ curve for AgFeAsSe₃ at temperatures of 220–250 K. The relationship between magnetization and temperature for AgFeAsSe₃ changes the shape of the curve below ~ 310 K, due to the material transition from the paramagnetic state to a state with magnetic ordering.




Fig. 3. Relationship between pressure and resistance for AgFeAsSe_3 and AgFeSbSe_3 if (a) there is no magnetic field and (b) if there is for AgFeAsSe_3 .

greatly. With allowance for experimental error, the field where the phase transition appears under high pressure does not change if arsenic is replaced with stibium.

ACKNOWLEDGMENTS

This work was partially funded by the federal target program Scientists and Science Teachers of an Innovative Russia, 2009–2013.

REFERENCES

1. Melnikova, N.V., Kheifets, O.L., and Babushkin, A.N., *Al'ternat. Energet. Ekol.*, 2007, no. 5, pp. 56–63.
2. Shakirov, E.F., Kheifets, O.L., Melnikova, N.V., and Babushkin, A.N., *Bull. Russ. Acad. Sci. Phys.*, 2012, vol. 76, no. 3, p. 351.
3. Kheifets, O.L., Filippov, A.L., Melnikova, N.V., and Babushkin, A.N., *Bull. Russ. Acad. Sci. Phys.*, 2012, vol. 76, no. 3, p. 385.
4. Kheifets, O.L., Shakirov, E.F., Melnikova, N.V., Filippov, A.L., and Nugaeva, L.L., *Fiz. Tekh. Poluprovodn.*, 2012, vol. 46, pp. 7996–7970.
5. Kheifets, O.L., Melnikova, N.V., Filippov, A.L., et al., *Fiz. Tverd. Tela*, 2012, vol. 54, no. 8, pp. 1466–1469.
6. Vereshchagin, L.F., Yakovlev, E.N., Vinogradov, B.V., et al., *High Temp. – High Press.*, 1974, vol. 6, p. 499.
7. Nugaeva, L.L., Electrical Conductivity, Acoustical and Magnetic Properties of Complex Chalcogenides and Oxides, *Cand. Sci. (Physmath.) Dissertation*, Sverdlovsk: Ural'sk. Gos. Univ. im. A.M. Gor'kogo, 1987.

Under pressures of ~ 25 and ~ 24 GPa, the electric properties of AgFeAsSe_3 and AgFeSbSe_3 change