

Polar Jahn-Teller centers and  
magnetic neutron scattering cross-section in copper oxides.

A.S. Moskvin\*, A.S. Ovchinnikov

\*Department of Theoretical Physics, Ural State University, 620083,  
Ekaterinburg, Russia

In the framework of the model of the polar singlet-triplet Jahn-Teller centers the cross-section is obtained for magnetic neutron scattering in high- $T_c$  cuprates. Multi-mode character of the  $CuO_4$  cluster ground manifold in the new phase of polar centers determines the dependence of magnetic form-factor on the local structure and charge state of the center. It is shown that magnetic inelastic neutron scattering in the system of the polar singlet-triplet Jahn-Teller centers permits to investigate the non-magnetic charge and structure excitations.

Corresponding author: Prof. A.S. Moskvin, Department of Physics,  
Ural State University, 620083, Ekaterinburg, Russia

Fax: +7-3432-615-978      E-mail: alexandr.moskvin@usu.ru

Key words: copper oxides, magnetic form-factor.

PACS codes: 75.40.Gb, 74.25.Ha

# 1 Introduction.

Unconventional properties of the oxides like  $YBa_2Cu_3O_{6+x}$ ,  $La_{2-x}Sr_xCuO_4$ ,  $(K, Ba)BiO_3$ ,  $La_{1-x}Sr_xMnO_3$ ,  $La_2CuO_{4+d}$ ,  $La_2NiO_{4+d}$  including systems with the high- $T_c$  superconductivity and colossal magnetoresistance reflect a result of the response of the system to the nonisovalent substitution that stabilizes phases providing the most effective screening of the charge inhomogeneity. These phases in oxides may involve novel unconventional molecular cluster configurations like the Jahn-Teller center [1] with anomalous high local polarizability and multi-mode behavior. The numerous experimental investigations show that the origin of the high- $T_c$  superconductivity and other unconventional physical properties of the copper oxides is connected with an active interplay of the whole set of the degrees of freedom including the charge, spin, orbital and structural modes under conditions of the strong charge inhomogeneity and granularity. Indirectly this is corroborated by the failures to explain more or less completely the unconventional behavior of copper oxides as


homogeneous systems within the "single-mode" approaches such as the spin-fluctuation, electron-phonon or purely electronic ones. An active interplay of the whole set of the modes is a natural element of the "multi-mode" scenario based on the so called "polar Jahn-Teller center model" proposed by one of the authors earlier [1, 2]. The  $CuO_4$ -clusters based copper oxides in this model are considered as systems of the local singlet bosons moving on the lattice composed from the singlet-triplet pseudo-Jahn-Teller (pseudo-JT) centers. An essential physics of cuprates within this scenario is connected with the multi-mode behavior and phase separation. An occurrence of the unconventional properties of the copper-oxygen  $CuO_4$  clusters as the basic elements of crystalline and electronic structure of the cuprates results in revision of many standard approaches. Below, we'll consider some features of the magnetic neutron scattering in the system of the polar pseudo-JT centers and obtain an expression for the appropriate cross-section.

It is worth to note that namely the magnetic inelastic neutron scattering together with the NMR and NQR stimulated the elabo-

ration of the well known model of spin fluctuations for the cuprates [3, 4] which is considered as the most promising and perspective for the HTSC mystery explanation. We'll show that the developed model reveals some new features of the magnetic inelastic neutron scattering in cuprates.

## 2 Polar singlet-triplet Jahn-Teller center model.

The  $CuO_4$ -clusters based copper oxides within the polar pseudo-JT centers model are considered as systems unstable with respect to the disproportionation reaction



with the creation of the system of the polar (hole  $[CuO_4]^{5-}$  or electron  $[CuO_4]^{7-}$ ) Jahn-Teller centers. These centers are distinguished by the so called S-boson or two electrons paired in the completely filled molecular orbital of the  $CuO_4$ -cluster. In other words, the new phase can be considered as a system of the local spinless bosons moving in the lattice of the hole JT centers or the generalized quantum

lattice bose-gas with the boson concentration near  $N_B = \frac{1}{2}$ . The Jahn-Teller structure of the polar centers provides the high stability of the disproportionated phase with the small probability of the recombination process. A near degeneracy within ( ${}^1A_{1g}, {}^{1,3}E_u$ )-manifold can create conditions for the anomalous strong electron-lattice correlations (pseudo-Jahn-Teller effect [5] ) with the active local displacement modes of the  $Q_{e_u}$ ,  $Q_{b_{1g}}$  and  $Q_{b_{2g}}$  types. In general, the pseudo-Jahn-Teller effect in the ( ${}^1A_{1g}, {}^{1,3}E_u$ )-manifold results in the formation of the four-well adiabatic potential of two symmetry types:  $E_u B_{1g}$  and  $E_u B_{2g}$ . In the first case we have four minima with the nonzero local displacements  $Q_{e_u} \neq 0$ ,  $Q_{b_{1g}} \neq 0$  for the hybrid copper-oxygen mode  $Q_{b_{1g}}$  and the purely oxygen mode  $Q_{e_u}$ . In the second case four wells correspond to the nonzero displacements of the  $Q_{e_u}$  and  $Q_{b_{2g}}$ -types. A type ( $E_u B_{1g}$  or  $E_u B_{2g}$ ) of the ground JT mode has the principal importance for the physics of the copper oxides. It is determined by the competition between the vibronic parameters for the  $Cu3d - O2p$  and  $O2p - O2p$ -bonds minimizing the  $E_u B_{1g}$  and  $E_u B_{2g}$ -modes, respectively. In the real systems, we

deal with a ground "rhombic"  $E_u B_{1g}$  -mode [6]. Fig. 1 gives the qualitative picture for the pseudo-JT effect in the hole  $[CuO_4]^{5-}$  cluster with illustrations of the cluster deformations in the  $E_u B_{1g}$  and  $E_u B_{2g}$  modes. In both cases we have to deal with the ground state JT quartets which undergoes the tunnel splitting to one doublet and two singlets.

The hole pseudo-JT center with its high polarizability can be a center of an effective local pairing with a formation of the local singlet boson or two electrons paired in completely filled molecular shell. The hole  $[CuO_4]_{PJT}^{5-}$  center with the local boson represents the unconventional electron center which is essentially distinguished from the "primitive"  $[CuO_4]^{7-}$  center considered as a non-degenerate system with the completely filled  $Cu3d$  and  $O2p$ -shells. A transfer from the hole to the electron pseudo-JT center because of charge fluctuations is accompanied generally by the change of the local bare parameters such as A-E-separations  $\Delta_{AE} = \varepsilon(^1E_u) - \varepsilon(^1A_{1g})$ , singlet-triplet separation  $\Delta_{ST} = \varepsilon(^3E_u) - \varepsilon(^1E_u)$  and also by the change of the ground JT mode ( $E_u B_{1g} \leftrightarrow E_u B_{2g}$ ).

In other words, the charge fluctuations in the phase of the pseudo-JT centers are strongly coupled with the local spin and structural fluctuations that results in complicated multimode behavior.

### 3 The magnetic neutron cross-section in pseudo-JT center system.

The neutron cross-section in the system of the pseudo-JT centers is determined by the common expression [7]

$$\frac{d^2\sigma}{d\Omega d\varepsilon} = \frac{1}{2\pi\hbar} \frac{p'}{p} (r_0\gamma)^2 \sum_{\alpha,\beta=x,y,z} \frac{1}{3} (\delta_{\alpha\beta} - e_\alpha e_\beta) \times$$

$$\sum_{l,l'} \sum_{\nu,\nu'=1,2} \int_{-\infty}^{+\infty} dt e^{-i\omega t} e^{-i\vec{q}(\vec{R}_{l'} - \vec{R}_l)} \langle s_{l'\nu'}^\beta e^{-i\vec{q}\vec{r}_{l'\nu'}} e^{i\vec{q}\vec{r}_{l\nu}(t)} s_{l\nu}^\alpha(t) \rangle, \quad (1)$$

where sums run over all pseudo-JT centers  $l, l'$  and over the holes of the separate pseudo-JT center  $\nu, \nu'$ ;  $\vec{s}_{l1}, \vec{s}_{l2}$  are the spins corresponding to the  $b_{1g}$  and  $e_u$  molecular orbitals of the  $[CuO_4]^{5-}$  cluster two-hole configuration;  $\vec{e} = \frac{\vec{q}}{q}$  is the unit scattering vector;  $r_0$  is the electromagnetic electron radius;  $\gamma = -1.913$  is the neutron magnetic moment written in terms of Borh's magneton  $\beta_n$ .

Within the  ${}^3E_u$  manifold the correlation function in (1) can be presented as

$$\langle S_l^\beta F^*(\vec{q}) F(\vec{q}, t) S_l^\alpha(t) \rangle, \quad (2)$$

where the total spin operator  $\vec{S}_l = \vec{s}_{1l} + \vec{s}_{2l}$  of the  $[CuO]_4^{5-}$  cluster were used. Taking into account the vibronic interaction the form-factor of magnetic neutron scattering

$$F(\vec{q}, t) = \frac{1}{2} \sum_{\nu=1,2} e^{i\vec{q}\vec{r}_\nu(t)} \quad (3)$$

takes the operator form within the  ${}^3E_u$  manifold, e.g. for the  $B_{1g}$ -type adiabatic potential of trivial vibronic  $E + (b_{1g} + b_{2g})$  problem [5] (see Fig. 2) without account of the  $pd$  and  $pp$  overlap integrals

$$\hat{F}(\vec{q}, t) = F_0(\vec{q}) + F_1(\vec{q})\hat{\sigma}^z(t), \quad (4)$$

where  $\sigma^z$  is Pauli's matrix,

$$\begin{aligned} \hat{F}_0(\vec{q}) = & \frac{1}{2}|c_d|^2 \langle d_{x^2-y^2} | e^{i\vec{q}\vec{r}} | d_{x^2-y^2} \rangle + \\ & \frac{|c_p|^2}{4} (\cos(q_x R) \langle p_x | e^{i\vec{q}\vec{r}} | p_x \rangle + \cos(q_y R) \langle p_y | e^{i\vec{q}\vec{r}} | p_y \rangle) + \\ & \frac{|c_\sigma|^2}{4} (\cos(q_x R) \langle p_x | e^{i\vec{q}\vec{r}} | p_x \rangle + \cos(q_y R) \langle p_y | e^{i\vec{q}\vec{r}} | p_y \rangle) + \\ & \frac{|c_\pi|^2}{4} (\cos(q_y R) \langle p_x | e^{i\vec{q}\vec{r}} | p_x \rangle + \cos(q_x R) \langle p_y | e^{i\vec{q}\vec{r}} | p_y \rangle), \end{aligned} \quad (5)$$

$$F_1(\vec{q}) = \frac{|c_\sigma|^2}{4}(\cos(q_x R)\langle p_x | e^{i\vec{q}\vec{r}} | p_x \rangle - \cos(q_y R)\langle p_y | e^{i\vec{q}\vec{r}} | p_y \rangle) + \frac{|c_\pi|^2}{4}(\cos(q_y R)\langle p_x | e^{i\vec{q}\vec{r}} | p_x \rangle - \cos(q_x R)\langle p_y | e^{i\vec{q}\vec{r}} | p_y \rangle). \quad (6)$$

Here  $R$  is the  $Cu - O$  distance ( $R \approx 2 \text{ \AA}$ ) and the matrix elements are

$$\langle p_{x,y} | e^{i\vec{q}\vec{r}} | p_{x,y} \rangle = \langle j_0(qr) \rangle_{2p} + \langle j_2(qr) \rangle_{2p} (C_0^2(\vec{q}) \mp \sqrt{\frac{3}{2}}(C_2^2(\vec{q}) + C_{-2}^2(\vec{q}))), \quad (7)$$

$$\langle d_{x^2-y^2} | e^{i\vec{q}\vec{r}} | d_{x^2-y^2} \rangle = \langle j_0(qr) \rangle_{3d} + \frac{10}{7} \langle j_2(qr) \rangle_{3d} C_0^2(\vec{q}) + \frac{3}{7} \langle j_4(qr) \rangle_{3d} (C_0^4(\vec{q}) + \sqrt{\frac{35}{2}}(C_4^4(\vec{q}) + C_{-4}^4(\vec{q}))). \quad (8)$$

The  $\langle j_l \rangle_{nk}$  in (7-8) is the radial average of the first kind Bessel function,  $C_m^l$  is the tensor spherical function. The coefficients  $c_d, c_p$  and  $c_\sigma, c_\pi$  obey to the usual relations

$$|c_d|^2 + |c_p|^2 = 1, \quad |c_\sigma|^2 + |c_\pi|^2 = 1. \quad (9)$$

These depend on the on site boson number  $\hat{N}$ , e.g.

$$|c_d|^2 = |c_d^{(0)}|^2 + (|c_d^{(1)}|^2 - |c_d^{(0)}|^2) \hat{N}, \quad (10)$$

and have different values for the electron ( $N = 1$ ) and hole ( $N = 0$ ) centers.

Note that the  $b_{1g}$ -hole contribution to the  $F_0(\vec{q})$  coincides formally with the form-factor of the  $b_{1g}$ -hole in the  $CuO_4^{6-}$ -center of the parent antiferromagnetic matrix

$$F(\vec{q}) = \langle b_{1g} | e^{i\vec{q}\vec{r}} | b_{1g} \rangle = |c_d|^2 \langle d_{x^2-y^2} | e^{i\vec{q}\vec{r}} | d_{x^2-y^2} \rangle + \frac{|c_p|^2}{2} (\cos(q_x R) \langle p_x | e^{i\vec{q}\vec{r}} | p_x \rangle + \cos(q_y R) \langle p_y | e^{i\vec{q}\vec{r}} | p_y \rangle). \quad (11)$$

The non-trivial contribution  $F_1\hat{\sigma}$  in the form-factor is caused only by the  $e_u$ -hole and has the anomalous  $\vec{q}$ -dependence with the nodes along the  $[1, 1]$ -direction of reciprocal lattice.

In general, the  $F_0(\vec{q})$ ,  $F_1(\vec{q})$  values depend on the boson density within the pseudo-JT center and could be considered as the boson number operators

$$F_0(\vec{q}) = F_0^{(0)}(\vec{q}) + F_0^{(1)}(\vec{q}) \hat{N}, \quad F_1(\vec{q}) = F_1^{(0)}(\vec{q}) + F_1^{(1)}(\vec{q}) \hat{N}. \quad (12)$$

In Fig. 3(a-g) we present the  $|F(\vec{q})|^2$  for the  $b_{1g}$ -hole in a parent compound, the  $|F_0(\vec{q})|^2$ ,  $F_0(\vec{q})F_1(\vec{q})$  and  $|F_1(\vec{q})|^2$  calculated using the known data [8] on the atomic  $Cu3d$  and  $O2p$  functions. We pay attention on the anomalous  $\vec{q}$ -dependence of the  $F_1(\vec{q})$  contribution connected with the local structure (vibronic JT) modes which is

responsible for the anisotropic fine structure of the full magnetic form-factor. This structure can be revealed experimentally even for the small  $F_1(\vec{q})$  values.

Finally, the magnetic neutron cross-section in the polar pseudo-JT centers system takes the form

$$\begin{aligned}
\frac{d^2\sigma}{d\Omega d\varepsilon} \sim & \sum_{\alpha,\beta=x,y,z} (\delta_{\alpha\beta} - e_\alpha e_\beta) \sum_m \sum_{m'} e^{-i\vec{q}\vec{R}_{m'}} e^{i\vec{q}\vec{R}_m} \int_{-\infty}^{\infty} dt e^{-i\omega t} \\
& \langle (F_0^{(0)}(-\vec{q}) + F_0^{(1)}(-\vec{q}) \hat{N}(m, 0) + \\
& [F_1^{(0)}(-\vec{q}) + F_1^{(1)}(-\vec{q}) \hat{N}(m, 0)] \sigma^z(m, 0)) \hat{S}^\alpha(m, 0), \\
& (F_0^{(0)}(\vec{q}) + F_0^{(1)}(\vec{q}) \hat{N}(m', t) + \\
& [F_1^{(0)}(\vec{q}) + F_1^{(1)}(\vec{q}) \hat{N}(m', t)] \sigma^z(m', t)) \hat{S}^\beta(m', t) \rangle, \quad (13)
\end{aligned}$$

where the hybrid "spin-charge-structure" correlation functions are presented. The standard approximation for the (13) implies a breaking apart the hybrid correlation functions, i.e.

$$\begin{aligned}
\langle S^\alpha(m, 0) \sigma^z(m, 0) \sigma^z(m', t) S^\beta(m', t) \rangle \approx \\
\langle S^\alpha(m, 0) S^\beta(m', t) \rangle \langle \sigma^z(m, 0) \sigma^z(m', t) \rangle \quad (14)
\end{aligned}$$

or

$$\begin{aligned} \langle S^\alpha(m, 0) \hat{N}(m, 0) \hat{N}(m', t) S^\beta(m', t) \rangle &\approx \\ \langle S^\alpha(m, 0) S^\beta(m', t) \rangle \langle \hat{N}(m, 0) \hat{N}(m', t) \rangle. &\quad (15) \end{aligned}$$

The operator structure of the magnetic neutron scattering, an appearance of the hybrid correlation functions in the appropriate cross-section directly points to the possibility to detect the non-magnetic structure and/or charge dynamic fluctuations by means of the magnetic inelastic neutron scattering. This effect displays itself distinctly in the spin subsystem transparency region far from the main spin excitations, when we can neglect the time dependence of the spin correlation function in the relations (14-15). For some cases the complex hybrid structure of the magnetic form-factor allows to explain by easily way the observed anomalies in the magnetic inelastic neutron scattering in cuprates. In particular, it explains an appearance of the strong inter-plane antiferromagnetic like correlations in the "bi-layer" systems such as  $YBa_2Cu_3O_{6+x}$  [9] that are natural for the charge and/or vibronic fluctuations, but improbable

for the pure spin fluctuations at a weak inter-plane exchange.

## References

- [1] A.S. Moskvina, JETP Lett. 58 (1993) 342.
- [2] A.S. Moskvina, N.N. Loshkareva, Yu.P. Suchorukov, M.A. Sidorov, A.A. Samokvalov, JETP 105 (1994) 967.
- [3] A.J. Millis, H. Monien, D. Pines, Phys. Rev. B 42 ( 1990) 167.
- [4] P. Monthoux, D. Pines, Phys. Rev. B 49 (1994) 4261.
- [5] I. B. Bersuker, V. Z. Polinger, Vibronic interactions in molecules and crystals. Springer-Verlag, 1989.
- [6] A.S. Moskvina, Yu.D. Panov, JETP 111 (1997) 644.
- [7] Yu.A. Izyumov, N.A. Chernoplekov, Magnitnaya neitronografia (Nauka, Moscow,1966).
- [8] Atomic Data and Nuclear Data Tables, 14 (1974).
- [9] P. Bourges, L.P. Regnault, Y. Sidis, C. Vettier, Phys. Rev. B 53 (1996) 876.

## Figure captions.

Fig. 1. The illustration of the ground state manifold splitting for the pseudo-JT center.

Fig. 2. The electron density distribution for the  ${}^{1,3}E_u$  term of the  $b_{1g}e_u(\sigma)$  configuration (left) and the  $b_{1g}e_u(\pi)$  one (right). The dark filling corresponds to the  $e_u$  orbitals and light filling does to the  $b_{1g}$  ones. The appropriate vibronic states  $\sigma_z = \pm\frac{1}{2}$  correspond to the  $B_{1g}$ -type JT mode.

3.  $\vec{q}$ -dependence (measured in  $\text{\AA}^{-1}$ ) of the magnetic form-factor  $|F(\vec{q})|^2$  for  $b_{1g}$ -hole in the parent compounds (a);  $|F_0(\vec{q})|^2$  at  $c_\sigma = 1/\sqrt{2}$ ,  $c_\pi = 1/\sqrt{2}$  (b) and  $c_\sigma = 1$ ,  $c_\pi = 0$  (c);  $F_0(\vec{q})F_1(\vec{q})$  at  $c_\sigma = 1/\sqrt{2}$ ,  $c_\pi = 1/\sqrt{2}$  (d) and  $c_\sigma = 1$ ,  $c_\pi = 0$  (e);  $|F_1(\vec{q})|^2$  at  $c_\sigma = 1/\sqrt{2}$ ,  $c_\pi = 1/\sqrt{2}$  (f) and  $c_\sigma = 1$ ,  $c_\pi = 0$  (g). It was taken  $c_d = 0.8$ ,  $c_p = 0.6$ ,  $q_z = 0$  for each case.

This figure "fig1.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>

This figure "fig2.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>

This figure "fig3.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>

This figure "fig4.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>

This figure "fig5.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>

This figure "fig6.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>

This figure "fig7.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>

This figure "fig8.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>

This figure "fig9.gif" is available in "gif" format from:

<http://arxiv.org/ps/cond-mat/9709033v1>